



TECHNICAL DATA SHEET Universal Hardener

Size 2.5 Litre/1 Litre

Code: U2KHG20-ST Code: U2KHG20-F Code: U2KHG20-XF

PROXL Generation 20 Universal Hardener has been developed for achieving superior results when used at a 2:1 mix ratio with 2K Acrylic Solid Colours and 2K Clearcoats. It is available in three speeds to cater for all types of repair and drying conditions.

Features and benefits

- High isocyanate content for long term durability
- Suitable for use with most 2K paint systems
- Available in three curing speeds

Drying times @ 20°C:

Mixed 2:1	U2KHG20-ST Standard	U2KHG20-F Fast	U2KHG20-XF Extra Fast
Dust Dry	1 Hour	1 Hour	30 Minutes
Dry to touch	2.5 Hours	1.5 Hours	1.2 Hours
Dry	5 Hours	4 Hours	3 Hours

Recommended use at ambient temperatures:

	Full Respray	Panel Respray	Spot Repair
U2KHG20-ST STANDARD	10°C - 25°C	10°C - 30°C	20°C - 30°C
U2KHG20-F FAST	Not Recommended	10°C - 25°C	10°C - 30°C
U2KHG20-XF EXTRA FAST	Not Recommended	10°C - 25°C	10°C - 25°C

Technical Information

Isocyanate Hardener
Recommended mixing ratio: 2:1
Specific weight of 940 g/l
39% Solid Content
574 g/l VOC

Environmentally sound

The products supplied by ProXL are 100% free of heavy metals and the caps and packaging are made of recyclable material.

Disposal

C ompletely emptied cans should be put in recycling skips or appropriate container.
C ans which are not empty should be disposed off as special refuse.

This application and technical information is given to the best of our knowledge. The notes mentioned herein are, however, non-binding and do not exempt you from own tests to see whether the products supplied by

us are suitable for your special application. The use and processing is beyond our control and therefore exclusively is the responsibility of the user.

