# PROXL PROTEXC CLEAR TEXTURE

### **FEATURES**

- Structural reproduction of damaged plastics and plastic parts
- Transparent colour for bright undercoats, black for dark undercoats
- Simple, time-saving application
- Suitable for exterior plastic car parts e.g. door frames, mirrors, tuning parts and bumpers as well as interiors e.g. dashboard, centre console, door panels and boot lining

#### PHYSICAL AND CHEMICAL DATA

- Basis of binder: Vinylcopolymer
- Colour: transparent
- Smell: solvent
- Degree of gloss: (at measurement angle 60° acc. to DIN 67530) glossy: >15 gloss units
- Efficiency: Depending on consistence and colour of the ground: 400 ml are sufficient for 1,0 - 1,5 m<sup>2</sup>
- Substrate:
  Damaged areas on all plastic parts inside and outside,
- Drying time (at 20°C, 50% relative air humidity):
  Dust-dry: after approx. 10 minutes
  Dry to touch: after approx. 30 minutes
  The drying time depends on surrounding temperature, air humidity and thickness of the applied coat.
- Temperature resistance: to 80°C
- Storage stability:
  10 years if appropriate storage provided (=10°-25°C, relative air humidity of max. 60%)
- Size:
- Aerosol cans, maximum nominal volume 400 ml
- VOC-value: 244,1g

#### ENVIRONMENT AND LABELLING

**Environmentally compatible Capella** is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

**Disposal:** Please mind the residue inside the containers. Completely emptied containers can be used for recycling. If cans are not emptied, they should be disposed off as "special refuse". **Labelling:** All products of capella comply with the current status of their labelling regulations. Classification and distinction takes place by the presently legal form of the **Globally Harmonized System of Classification and Labelling of Chemicals** (GHS) or rather by CLP 1272/2008/EG regulations. Our safety data sheets comply with the current form of REACH 1907/2006/EG, article 31 und appendix II,

## **USING INSTRUCTIONS**

Before use, carefully read and observe the warning texts on the label! Anwendung

- Clean surface thoroughly
- Damaged area must be dry and free of dust and grease
- Shake can vigorously for 2 minutes
- Carry out spray test
- The structural density and effect is dependent on the numer of coats and the spraying distance
- Apply several thin coats to get desired texture
- Recoat once it has dried for approx. 15-20 min (20°C)
- Must be recoated
- For professional use only
- Wear an appropriate respirator (recommended type A2/P3)

