

XUHT – HIGH TEMP PAINT MATT

PRODUCT DESCRIPTION

A high temperature resistance coating

FEATURES AND BENEFITS

- Excellent temperature resistance up to 200°C

TYPICAL AREAS OF USE

Where a high temperature resistant coating is required

SUITABLE SUBSTRATES & PREPARATION

Iron surfaces that are free of dust, grease & moisture

MIXING INSTRUCTIONS

Dilute 10% with T1 thinners

APPLICATION GUIDE

Conventional or Airless Spray equipment
1-2 coats to reach the desired thickness



XUHT – HIGH TEMP PAINT MATT

DRYING TIMES AND COVERAGE

Drying Times @ 20°C:

Flash off: 10 mins

Dust free: 20-30 mins

Through dry: 24 hrs

Full cure: 7 days

Typical Dry Film Thickness: 40 microns

Covering Capacity:

Covering Capacity: 9m² per litre @ 40um DFT

CHEMICAL DATA

Composition: Phenyl silicone alkyd

Volume of solids: 60%

Specific Gravity: 1.4

VOC: 379 g/l

HEALTH AND SAFETY

Please refer to the MSDS

ENVIROMENTAL

The products supplied by INDURA are 100% free of heavy metals and the caps and packaging are made of recyclable material.

DISPOSAL

Completely emptied cans should be put in recycling skips or appropriate container. Cans which are not empty should be disposed of as special refuse.

DISCLAIMER OF LIABILITY

The information contained in this Technical Data Sheet is correct to the best of our knowledge, however, you must satisfy yourselves that the product is suitable for your needs by way of your independent testing or other processes. Alpha Coatings Limited trading as Capella Solutions Group makes no warranty, representation, or guarantee regarding the information contained in the Technical Data Sheet or the suitability of its products and services for any particular purpose, nor does Alpha Coatings Limited trading as Capella Solutions Group assume liability arising out of the application or use of any product(s) other than any liability which cannot be limited by law including but not limited to liability for: (a) death or personal injury caused by negligence; (b) fraud or fraudulent misrepresentation; and (c) breach of the terms implied by section 12 of the Sales of Goods Act 1979, in such circumstances Alpha Coatings Limited trading as Capella Solutions Group total liability shall not exceed the cost of the product(s). Alpha Coatings Limited trading as Capella Solutions Group's total liability includes liability in contract, tort, negligence, breach of statutory duty, or otherwise.