

# C090 2K Plasticiser Matt

---

## Description:

C090 2K Plasticiser Matt is a universal plasticizer for all MS and VOC topcoat systems. It is suitable for Eclipse filler and plastic finishes. C090 demonstrate high long-term elasticity.

---

## Preparation:

- Can be used for all car plastic panels.
- Add 15% of plasticiser to topcoats, clearcoats and fillers with medium and hard plastics.
- Add 30% of plasticiser to topcoats, clearcoats and fillers with soft plastics.

addition of C090 to 2k clear	Gloss level at 60 degrees
50%	75-85%
100%	65-75%
150%	50-60%
200%	10-20%

---

**Flash Point:** 27° C /80.6° F

---

**Specific Gravity:** 1.032 g/cm<sup>3</sup>

---

**Solids Content:** 46.8 Weight %

---

**Cleaning the Equipment:** Clean after use with cleaning thinner.

---

## IMPORTANT REMARKS:

- Eclipse 2K Plasticizer Matt must be included before the addition of 2K hardener.
  - To optimize the sanding properties the plasticized fillers should be dried 45 min/60-65 ° C panel temperatures. C090 may be added in a maximum proportion of 1:1 for maximum plasticizing effect.
  - When C090 is added to Eclipse 2K systems, it slows down the drying.
- 

## SAFETY:

Refer to Material Safety Data Sheet (MSDS) for complete safety instructions. The technical data sheet listed has been compiled in good faith for your convenience and guidance. No warranty, expressed or implied, is intended or given by the information on this sheet.

---