

HB-1 High Build Primer

Products Characteristics

- Very fast drying
- Smooth non-porous finish
- Good adhesion onto bare metal
- Can be over coated with any topcoat (Water based or solvent based)
- Excellent coverage and filling properties
- Easy to sand, both wet and dry (from 400 grit)



Properties

Density		0.778 kg/lit
Coverage		15.6m ² per lit
Drying times	Dust Free	5 - 10 minutes
	Touch Dry	15 minutes
	Overcoat able	30 minutes

Surface Preparation

- The surface must be free from all contamination including rust, grease and moisture.
- Apply only as a thin film. Not suitable for electrostatic spray equipment.
- Before use, carefully read and note the warning text on the label

DISCLAIMER OF LIABILITY

The information contained in this Technical Data Sheet is correct to the best of Alpha Coatings Limited trading as Capella Solutions Group's ("Capella") knowledge, however, you must satisfy yourselves that the Goods are suitable for your needs by way of your independent testing or other processes. Capella makes no warranty, representation, or guarantee regarding the information contained in the Technical Data Sheet or the suitability of its products and services for any particular purpose, nor does Capella assume liability arising out of the application or use of the Goods other than any liability which cannot be limited by law including but not limited to liability for: (a) death or personal injury caused by negligence; (b) fraud or fraudulent misrepresentation; and (c) breach of the terms implied by section 12 of the Sales of Goods Act 1979, in such circumstances Capella's total liability shall not exceed the cost of the Goods. Capella's total liability includes liability in contract, tort, negligence, breach of statutory duty, or otherwise. It is the Customer's responsibility to ensure that the guidance on the Technical Data Sheet is followed.

For uses not regulated by the Directive
2004/42/EC

Second Avenue, Chatham, Kent, ME4 5AU
t: +44 (0)1634 823900
f: +44 (0)1634 813807
e: sales@capellasolutionsgroup.com